



THERMAL PERFORMANCE VALUES 900 SERIES > DOUBLE HUNG(see notes at end)

DOUBLE HUNG	U Value	SHGC	Vt	ER
Dual Pane - Low-E / Hard Coat	0.34	0.57	0.59	30
Dual Pane - Low-E / Soft Coat	0.31	0.33	0.56	20
Dual Pane - Low-E 366	0.30	0.22	0.51	14
Triple Pane - Low-E / Hard Coat x 2*	0.24	0.45	0.50	34
Triple Pane - Low-E / Soft Coat x 2*	0.22	0.28	0.45	28

Note: All values have been verified by the NFRC and Energy Star Canada. The reader is cautioned that test results should be used for comparison purposes only. Results are size and installation dependent.

For recommendations as to what glazing configurations are best suited for your application, please feel free to contact us.

For a full listing of thermal performance values, visit www.NFRC.org. All information can be found in the "Certified Products Directory". Please feel free to contact us if any assistance is required.

INLINE also complies with all North American Energy Star zoning requirements.



* Krypton Gas Fill

© Copyright Inline Fiberglass Ltd. of Toronto, Canada 2008.

Unless otherwise shown, all ratings shown with thermal edge spacer, argon fill, foam filled sash and frame, soft coats are CD272 and hard coats are Pilkington Energy Advantage (also called LOF)